

obtained. Furthermore, also from the viewpoint of adhesiveness between the reinforcing fibers and the matrix resin, a relationship between a melting point, $T_m(M)$, of a polypropylene-based resin which is the matrix resin and a melting point, $T_m(F)$, of a polypropylene-based resin which is the material forming the reinforcing fibers is extremely important and the melting temperatures must have the aforementioned relationship, $T_m(F) - T_m(M) > 10^\circ\text{C}$.
